

**ABSTRACT**

A process and system for processing a thin film sample are provided. In particular, a beam generator can be controlled to emit at least one beam pulse. The beam pulse is then masked to produce at least one masked beam pulse, which is used to irradiate at least one portion of the thin film sample. With the at least one masked beam pulse, the portion of the film sample is irradiated with sufficient intensity for such portion to later crystallize. This portion of the film sample is allowed to crystallize so as to be composed of a first area and a second area. Upon the crystallization thereof, the first area includes a first set of grains, and the second area includes a second set of grains whose at least one characteristic is different from at least one characteristic of the second set of grains. The first area surrounds the second area, and is configured to allow an active region of a thin-film transistor ("TFT") to be provided at a distance therefrom.

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
26 February 2004 (26.02.2004)


PCT

(10) International Publication Number  
**WO 2004/017381 A2**

- (51) International Patent Classification<sup>7</sup>: **H01L** [US/US]; 520 West 114th Street, Apt. 74, New York, NY 10025 (US).
- (21) International Application Number: **PCT/US2003/025954** (74) Agents: **TANG, Henry et al.**; Baker Botts L.L.P., 30 Rockefeller Plaza, New York, NY 10112-4498 (US).
- (22) International Filing Date: 19 August 2003 (19.08.2003) (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 60/405,085 19 August 2002 (19.08.2002) US
- (71) Applicant (*for all designated States except US*): **THE TRUSTEES OF COLUMBIA UNIVERSITY IN THE CITY OF NEW YORK** [US/US]; 116th Street and Broadway, New York, NY 10027 (US).
- (72) Inventor; and (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (75) Inventor/Applicant (*for US only*): **IM, James, S.**

[Continued on next page]

(54) Title: PROCESS AND SYSTEM FOR LASER CRYSTALLIZATION PROCESSING OF FILM REGIONS ON A SUBSTRATE TO MINIMIZE EDGE AREAS, AND STRUCTURE OF SUCH FILM REGIONS



(57) Abstract: A process and system for processing a thin film sample are provided. In particular, a beam generator can be controlled to emit at least one beam pulse. The beam pulse is then masked to produce at least one masked beam pulse, which is used to irradiate at least one portion of the thin film sample. With the at least one masked beam pulse, the portion of the film sample is irradiated with sufficient intensity for such portion to later crystallize. This portion of the film sample is allowed to crystallize so as to be composed of a first area and a second area. Upon the crystallization thereof, the first area includes a first set of grains, and the second area includes a second set of grains whose at least one characteristic is different from at least one characteristic of the second set of grains. The first area surrounds the second area, and is configured to allow an active region of a thin-film transistor ("TFT") to be provided at a distance therefrom.

